



# TECHNICAL DATA SHEET

## 85% Virgin PTFE, 15% Graphite

### PHYSICAL PROPERTIES

Product Code: GF1045

Low Flow Polytetrafluoroethylene (nff)

Test Method	Properties	Units	Typical Value
ASTM 4745-14	Tensile	PSI	2000 min.
ASTM 4745-14	Elongation	%	100 min.
ASTM D2240	Shore Hardness	Shore D	55-63
ASTM D792-08	Specific Gravity	G/CC	2.100-2.200
ASTM 4745-14	Density	g/l	300 min.
ASTM D648	Service Temp.	°F	500°F

## GF1045 MEETS AMS3678/2 STANDARD

The above information is, to the best of our knowledge, true and accurate. No warranty, expressed or implied, is made or intended. The use of this product should be determined by the user based on their appraisal.

Contact:

Gemini Pro-Lon LLC

855-521-7833

sales@gpltx.com