



TECHNICAL DATA SHEET

95% Virgin PTFE, 5% Ekonol

PHYSICAL PROPERTIES

Product Code: GF1132

Low Flow Polytetrafluoroethylene (nff)

Test Method	Properties	Units	Typical Value
ASTM 4745-14	Tensile	PSI	2900 min.
ASTM 4745-14	Elongation	%	250 min.
GEMINI	Shore Hardness	D	56 +/- 3
ASTM D792-08	Specific Gravity	G/CC	2.0-2.150

Ekonol extends the life of PTFE parts. When PTFE is filled with Ekonol, the thermal stability, creep resistance, and dimensional stability are greatly enhanced. A good fit for seals, bearings, and rotors.

The above information is, to the best of our knowledge, true and accurate. No warranty, expressed or implied, is made or intended. The use of this product should be determined by the user based on their appraisal.

Contact:

Gemini Pro-Lon

855-521-7833

sales@gpltx.com