



## TECHNICAL DATA SHEET

### *GemFlon Virgin Molding Powder*

#### **PHYSICAL PROPERTIES**

Product Code: GF GemFlon

Low Flow Polytetrafluoroethylene (nff)

Test Method	Properties	Units	Typical Value
ASTM 4745-14	Tensile	PSI	5076
ASTM 4745-14	Elongation	%	300
ASTM D-2240	Shore Hardness	D	53
ASTM D792-08	Specific Gravity	G/CC	2.150

GemFlon virgin PTFE is designed for compression molding of billets, tubes, and rods. Virgin PTFE should be stored @ 74°F for best results.

The above information is to the best of our knowledge, true and accurate. No warranty, expressed or implied, is made or intended. The use of this product should be determined by the user based on their appraisal.

Contact:

**Gemini Pro-Lon LLC**

855-521-7833

sales@gpltx.com