

**Pro-Lon PTFE Products** 

## TECHNICAL DATA SHEET Virgin Skived PTFE Sheet

PHYSICAL PROPERTIES

Virgin Type 1

Test Method	Properties	Units	Typical Value
ASTM D3308-12	Tensile	PSI	4000 min.
ASTM D3308-12	Elongation	%	300 min.
ASTM D785	Shore Hardness	D	58-62
ASTM D3308-12	Thickness Tolerance	In.	.0151" – 0.400": .0015" 0.401" – 0.125": .0050"

Type 1 Virgin Skived PTFE Sheet is used for exacting electrical, mechanical ,and chemical applications.

The above information is, to the best of our knowledge, true and accurate. No warranty, expressed or implied, is made or intended. The use of this product should be determined by the user, based on their appraisal.

Contact: Gemini Pro-Lon LLC 855-521-7833 jimmie@gpltx.com